



Dr. Fixit Super Latex

SBR LATEX FOR WATERPROOFING & REPAIRS

Description

Dr. Fixit Super Latex is based on modified Styrene butadiene latex used for high performance applications in waterproofing and repairs. It is used for repairs of spalled concrete such as – floors, columns, beams, chhajjas, slabs & waterproofing of toilets & bathrooms & terraces. It bonds strongly to old & new concrete & plaster.

Typical Applications

- **As a bond coat** - Plaster to plaster, concrete-to-concrete, plaster to concrete for plastering over brick masonry. Bonding coat & mortar for tiles & panels, underlays for special finishes such as top rendering coat for chemical resistant floors.
- **As waterproofing** - Waterproofing of small roof terraces, sunken portions of toilet & bathrooms, chajjas & lift pits, balconies & staircase.
- **As crack repair** - Repairs of plaster cracks more than 5 mm & in gaps developed between masonry and RCC members.
- **As rebar coating** - Coating for prevention of corrosion over rebars.
- **For Cladding** - Fixing or refixing of slip bricks, tiles, stones & marble bedding.
- **As external rendering** - Weatherproof & frost resistant render, high wear & erosion resistant render. As bonding slurry coat for pin hole treatment on concrete surface & as repair mortar for overhead applications.

Features

- **Multipurpose** - It is multipurpose & economical product, easy to use
- **Cracking** - It prevents cracking by improving flexural strength
- **Hardness** - Improves the hardness & prevents dust generation
- **Shrinkage** - Reduces drying & aging shrinkage cracks
- **Bonding** - Bonds strongly to concrete, masonry, stone work, plasters, steel & most of the building materials.
- **Erosion & corrosion** - Improves erosion resistance & prevents corrosion.
- **Abrasion resistance** - Improves abrasion resistance of cement mix.
- **Waterproofing** - Prevents leakage & dampness.
- **Durability** - Enhances strength of a repair mortar & provides durability.
- **Rebound loss** - Less material wastage- material does not fall back/ rebound, when used as bonding agent.
- **Coverage** - Excellent Coverage -70-80 sq.ft per kg/ in 2 coats, hence economical.

Packaging

200 & 500 g, 1, 5 & 20 Kg

Method of Application

1 SURFACE PREPERATION

- Clean the surface with wire brush or scrubber to remove hidden dirt, loose particles, laitance, & dust. Degrease the surface by using suitable solvents.
- Repair the concrete spalled portion by saw cutting the extreme edges of the repair location to a depth of at least 10 mm to avoid featheredging & to provides strong substrate.
- Clean the concrete surface to remove any contamination where breaking is not possible. Roughen the surface by light scabbling or grit blasting.
- Expose corroded rebars in the repairing area fully. Remove all loose scales & corrosion deposits & immediately clean the surface.



Application mixing

| Sr. No. | AREAS OF APPLICATION | MIX (SUPER LATEX : WATER : CEMENT) | METHOD OF APPLICATION |
|---------|--|--|---|
| 1 | As bond coat | 1 : 4 : 7 | <ul style="list-style-type: none"> Apply a single coat of the mixed quantity of Dr. Fixit Super Latex. When coat is tacky, apply the plaster or concrete according to the situation. Always add cement to the liquid (Dr. Fixit Super Latex : water = 1 : 4). |
| 2 | As waterproof coating | 1 : 4 : 7 | <ul style="list-style-type: none"> Brush apply the 1st coat. Apply 2nd coat after 1st coat is dry approximately 4-6 hrs between two coats. Overlay the 2nd coat with screed/plaster for protection and finish. |
| 3 | Rebars coating | 1 : 4 : 7 | <ul style="list-style-type: none"> Rusted rebars must be thoroughly scraped, by mechanical means if required. Brush apply a single coat of prepared mix over the rebars. Apply concrete/mortar when the coat is tacky. |
| 4 | For 'salt petre'-free plaster Brick masonry | 1 : 4 : 7 | <ul style="list-style-type: none"> Brush apply the 1st coat on brick. Apply 2nd coat after 1st coat is dry. When 2nd coat is tacky, place plaster as per instruction in no. 5 |
| 5 | Renders, Patching & Crack Repair Mortar | 5 kg Dr. Fixit Super Latex +15 ltr Water 50 kg Cement + 150 kg Sand | <ul style="list-style-type: none"> Mix 5 kg of Dr. Fixit Super Latex with pre-measured water for 50 kg of cement. Use this mix to add to the recommended dry mortar mixes. Mortar mixes may be as rich as 1:3 (cement: sand) Keep water-cement ratio in Mortar as low as 0.4 but not more than 0.45. Clean the cracked area properly of all loose materials. Wet the crack completely using a bottle spray. Apply a single coat as a bond coat prior to the crack filling of the Dr. Fixit Super Latex as per the mixing proportions mentioned earlier. Fill the crack with above prepared mortar. Compact it into the crack fully and trowel finish to level. |
| 6 | As waterproof plaster | 50 kg OPC cement 150 kg Sand 1 kg Super Latex 20 ltr Water | <ul style="list-style-type: none"> Mix 1 kg of Dr. Fixit Super Latex with pre-measured water for 50 kg of cement. Use this mix to add to the recommended dry plaster mixes. Plaster mixes may be as rich as 1:3 (cement : sand) Keep water-cement ratio in Plaster as low as 0.4 but not more than 0.45. For better application apply a bond coat with super latex as suggested earlier. 2nd and final layer of plaster must not be mixed with Dr. Fixit Super latex. Add Dr. Fixit Pidiproof LW+ to the second coat plaster. Take care to scratch-key the 1st coat surface for effective bond with the 2nd coat. |

Precautions & Limitations

- Recommended dosage to be followed to achieve desired results.
- When working in hot temperature conditions, extra water may be added to the repair mortar to compensate for the evaporation loss & make the mortar workable.

Technical Information

| PROPERTIES | RESULTS |
|----------------------------------|-------------------------------|
| Appearance | Free flowing liquid |
| Colour | Milky white |
| Specific Gravity @30°C. gms / ml | 1.02 ± 0.02 |
| Non Volatile matter, % | 42 - 44 |
| PH value | 7 - 9 |
| Bond strength, N/sq mm | 5 |
| Chemical resistance | Resists mild acids & alkalies |
| Freeze thaw resistance | Excellent |

Coverage

For Bonding & waterproofing applications

- 1 kg of super latex will cover 70 - 80 sq. ft. area in 2 coats for a proportion mix 1 : 4 : 7 (Super Latex : Water : Cement).

Recommendations for other applications are given in above tables.

Shelf Life

- Best before one and half years from the date manufacture when in sealed pack and stored under proper condition.
- Store in a cool & dry place in unopened condition away from direct sunlight.

Health & Safety

- Use rubber hand gloves & safety goggles, while using Dr. Fixit Super Latex.
- In case of contact with skin, wash with plenty of water.
- Keep out of reach of children's.

Other Products Categories available

Dr. Fixit brings you the widest range of Construction Chemicals



Pidilite Industries Limited
 Construction Chemicals Division
 Ramkrishna Mandir Road, Post Box No. 17411
 Andheri (E) Mumbai 400059 INDIA
 Tel +91-22-2835 7000 • Fax +91-22-2835 7008
 www.drfixit.co.in • info@drfixit.co.in
 Dr. Fixit Advice Centre (Toll Free No.) 1800 209 5504

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.